



2870 CRESTWOOD BLVD. STE B
IRONDALE, AL 35210
205-857-0040



DEFENDER

DEFENDER EZ25

TECHNICAL DATA SHEET

DESCRIPTION

Defender EZ25 is a two-component, 1:1, 100% solids, fast set, liquid applied, modified polyurea-liner system for metal, concrete, fiberglass and wood surfaces.

FEATURES

- Abrasion and Impact Resistant
- Chemical Resistance
- High Build
- Low-Temperature Flexibility
- Quick Drying
- Seamless
- Tough and Elastomeric

TYPICAL USES

- Boat Linings
- Cargo Holds
- Cargo Liners
- Containment Areas
- Encapsulation of Fiberglass Bodies and Polystyrene Foams
- Horse Trailers
- Industrial Floorings
- Truck-Bed Liner
- Utility Vehicles
- Walkways
- Waterproof Decking

PACKAGING

10-Gallon Kit

5 gallons Side-A (Isocyanate side) and 5 gallons Side-B (Resin side)

100-Gallon Kit

50 gallons Side-A (Isocyanate side) and 50 gallons Side-B (Resin side)



2870 CRESTWOOD BLVD. STE B
IRONDALE, AL 35210
205-857-0040



DEFENDER

DEFENDER EZ25

TECHNICAL DATA SHEET

TECHNICAL DATA

BASED ON DRAW DOWN FILM

Mix Ratio by Volume	1A: 1B
Pot Life @ 150°F (65.5°C), 50% R.H.	2-4 seconds
Tack Free Time	10-30 seconds
Recoat Time	0 - 12 hours
Viscosity at 150-160°F (66.5-71°C) Side-A Side-B	120 ± 20 cps 200 ± 20 cps
Density (Side A & B Combined)	9.12 lbs/gal
Flash Point	> 200°F (93.3°C)
Hardness, ASTM D-2240	55 ± 5 Shore D
Tensile Strength, ASTM D-412*	2800 ± 200 psi 19.31 ± 1.37 MPa
Elongation, ASTM D-412*	200 ± 20%
Tear Strength, ASTM D-624*	400 ± 50 pli 69.93 ± 8.8 kNm
Service Temperature - Dry	-20°F to 250°F -4.0°C to 93°C
Water Vapor Permeability ASTM E96	0.69 Perms

(*These physical properties from sample sprayed with Graco Foam Cat 200 @ 2000 psi minimum, with Gusmer Gx7-400 mechanical purge gun @ 150-160°F (65°C to 71°C). Different machine and parameter will change these properties. User should perform their own independent testing as properties are approximate).

COLORS

Clear/Neutral. Custom colors are available upon request. Color Packs, when used, must be added to Resin side.

Due to its aromatic composition, Defender EZ25 will tend to yellow or darken in color and will become flat after exposure to UV light. Defender EZ25 may be top-coated within 12 hours of application with an aliphatic polyurethane/polyurea/polyaspartic coating for a colorfast finish.



2870 CRESTWOOD BLVD. STE B
IRONDALE, AL 35210
205-857-0040



DEFENDER

DEFENDER EZ25

TECHNICAL DATA SHEET

COVERAGE

Defender EZ25 may be applied at any rate to achieve desired thickness. Theoretical coverage for 1 mil (0.254 microns) thickness is one gallon per 1600 sqft (3.78 liters per 149 sqm). Estimating Formula: $(1600 \text{ sqft per gal} / \text{Dry Mil Thickness}) \times \text{Solids Content} = \text{Application Rate per gallon}$.

SURFACE PREPARATION

In general, coating performance and adhesion are directly proportional to surface preparation. Most failures in the performance of surface coatings can be attributed to poor surface preparation. Polyurea coatings rely on the structural strength of the substrate to which they are applied. All surfaces must be free of dust, dirt, oil, grease, rust, corrosion and other contaminants. When coating previously used substrates, it is important to consider the possibility of substrate absorption, which may affect the adhesion of the coating system, regardless of the surface preparation. UMI Coatings recognizes the potential for unique substrates from one project to another. The following information is for general reference. For project specific questions, contact UMI Coatings.

MIXING

Defender EZ25 may NOT be diluted under any circumstances. Thoroughly mix Defender EZ25 Side-B (Resin side) with air driven power equipment until a homogeneous mixture and color is achieved.

APPLICATION

Both Side-A and Side-B materials should be preconditioned to 80-90°F (27-32°C) before application. Recommended surface temperature must be at least 5°F (3°C) above the dew point. Defender EZ25 should be applied using a plural component, heated, high pressure 1:1 spray mixing equipment like Graco's Reactor, Exp-2 or other equivalent machine may be used. Both Side-A and Side-B materials should be sprayed at a minimum of 2000 psi and at temperatures above 150°F (66°C). Adequate pressure and temperature should be maintained at all times. Defender EZ25 should be sprayed in smooth, multidirectional passes to improve uniform thickness and appearance.

EQUIPMENT CLEAN UP

Equipment should be cleaned with Defender Flush immediately after use.



2870 CRESTWOOD BLVD. STE B
IRONDALE, AL 35210
205-857-0040



DEFENDER

DEFENDER EZ25

TECHNICAL DATA SHEET

STORAGE

Defender EZ25 has a shelf life of one (1) year from date of manufacture in original, factory-sealed containers when stored indoors at a temperature between 60-95°F (15-35°C). Side-A and Side-B drums are recommended to be stored above 60°F (15°C). Avoid freezing temperatures. Store drums on wooden pallets to avoid direct contact with the ground. If stored for a long period of time, rotate Side-A and Side-B drums regularly.

LIMITATIONS

Do not open until ready to use. Both Side-A and Side-B containers must be fitted with a desiccant device during use.

Warning: This product contains Isocyanates and Curative Material.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy themselves, by their own information and test, to determine suitability of the product for their own intended use, application and job situation and user assumes all risk and liability resulting from their use of the product. We do not suggest or guarantee that any hazard listed herein are the only ones which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and UMI Coatings makes no claim that these tests or any other tests, accurately represent all environments.